29

JC17 Rec'd PCT/PTO 3/64MA 2005

### ABSTRACT

An electrolytic capacitor having a low impedance characteristic, having a high withstand voltage characteristic of 100V class, wherein the electrolytic capacitor provides an excellent high temperature life characteristic and an excellent leakage characteristic. The electrolyte solution containing the aluminum tetrafluoride salt is used. Moreover, the ceramics coating layer or the insulating synthetic resin layer is formed at a contact portion with the sealing component of the rivet or the cathode leading means. Alternatively, a partial cross-linking peroxide butyl rubber that added peroxide as cross-linking agent to a butyl rubber polymer comprised of isobutylene, isoprene, and divinylbenzene copolymer is used as the sealing member. The electrolytic capacitor of the present invention has a low impedance characteristic, a high withstand voltage characteristic, and an excellent high temperature life characteristic.

## (12)特許協力条約に基づいて公開された国際出願

### (19) 世界知的所有權機関 国際事務局



# - 12017 MARINE DE LOCATO DE LO

## (43) 国際公開日 2004 年5 月21 日 (21.05.2004)

PCT

## (10) 国際公開番号 WO 2004/042757 A1

(51)	国際特許分類":	H01G 9/035, 9/008, 9/10, 9	9/04	
(21)	国際出願番号:	PCT/JP2003/014216		
(22)	国際出願日:	2003年11月7日(07.11.2003)		
(25)	国際出願の言語:	日本語		
(26)	国際公開の言語:	日本	香	
(30)	優先権データ:	00/0 <b>2</b> 1 80 5 (00 1 00 00	_	
	特願2002-326010	2002年11月8日(08.11.2002)	æ	
	特顯2002-326011	2002年11月8日(08.11.2002)	JР	
	特顯2002-326019	2002年11月8日(08.11.2002)	JР	
	特願2002-326028	2002年11月8日(08.11.2002)	JР	

(71) 出願人 (米国を除く全ての指定国について): 日本ケミコン株式会社 (NIPPON CHEMI-CON CORPORATION) [JP/JP]; 〒198-8501 東京都 青梅市 東青梅1丁目167番地の1 Tokyo (JP). 三菱化学株式会社 (MITSUBISHI CHEMICAL CORPORATION) [JP/JP]; 〒108-0014 東京都港区 芝五丁目33番8号 Tokyo (JP).


(72) 発明者; および

(75) 発明者/出願人 (米国についてのみ): 小澤 正 (OZAWA,Masashi) [JP/JP]; 〒198-8501 東京都 青梅 市東青梅1丁目167番地の1 日本ケミコン株 式会社内 Tokyo (JP). 武田 政幸 (TAKEDA,Masayuki)

/続葉有/

(54) Tille: ELECTROLYTIC CAPACITOR

#### (54) 発明の名称: 電解コンデンサ



(57) Abstract: An electrolytic capacitor having a low impedance characteristic, a high breakdown voltage characteristic of the order of 100 V, a favorable electrolyte leakage characteristic, and a favorable high-temperature life characteristic. The electrolyte contains aluminum tetrafluorate. A ceramic coating layer or an insulating synthetic resin layer is formed on cathode lead-out means or on a contact portion of a rivet which portion is in contact with a sealing member. The scaler is made of a peroxide partially crosslinked butyl rubber prepared by adding a peroxide as a cross linker to a butyl rubber polymer comprising a copolymer of isobutylenc, isoprene, and divinylbenzene. Thus, an electrolytic capacitor having the above characteristics is provided.

(57) 要約: 低インピーダンス 特性を有し、さらに100V級 の高耐電圧特性を有し、漏液特 性、高温寿命特性も良好な電解 コンデンサを提供する。四弗化 アルミニウム塩を含む電解液を 用いるとともに、陰極引出し手 段またはリベットの封口部材と

、の接触部分に、セラミックスコーティング層または絶縁性合成樹脂層を形成、または封口体としてイソブチレンと )イソプレンとジピニルベンゼンとの共重合

/続菜有/